

## LK-RX 22 H

**LK- RX 22 H Methyl Hydrogen polysiloxane fluid**

### FEATURES

- Cure to give a durable film.
- Can be diluted in solvents, for better dispersion.
- Non-toxic in nature
- Colorless in nature
- Effective at very low concentration.

### APPLICATIONS

- In Hydrosilylation reaction
- Basic raw material for silicone – carbon bond reactions

### PRODUCT CHARECTERISTICS

Product Name	Specific Gravity 25° C	Refractive Index 25° C	Viscosity at 25° C in cps (LV1,60 Rnm)	% Volatile content at 110° C 1 hr	Appearance	H Content by Weight
LK- RX 22 D	0.96– 1.01	1.385– 1.400	12 – 20	7 max	Clear colorless Liquid	1.5 - 1.6

<sup>1</sup> Typical Values – Should not be considered as specifications.

### PACKING

50 kg H.D.P.E. carboys and 200-kg drums.

### SHELF LIFE

24 months in the original container from the date of production when stored below 40 deg.C.

## **STORAGE & HANDLING**

***LK-RX 22 may evolve hydrogen gas in presence of catalyst and heat, when comes in contact with “HO-R” where R = alkyl, aryl, H, metal.***

***Catalysts: - Bases, acids, heavy metal salts, polar ionic salts, certain transition metal salts. For safe use of product refer MSDS of product.***

The information provided to the customers in this data sheet is intended as a guideline and is provided in good faith. The Information is believed to be accurate. Changes may occur from system to system as methods of use and conditions are beyond our control, hence users are requested to evaluate the recommendations before actual application to get desired performance.

ELKAY CHEMICALS PVT. LTD. (ELKAY) Main Plant Office (MIDC, Bhosari) exclusively can provide you with a specific written warranty for a particular use. In the absence of this, ELKAY gives the sole warranty that the product (or products) supplied will meet its sales specifications (not provided on this sheet). ELKAY disclaims any other expressed or implied warranty. For current or required specifications, please contact your ELKAY distributor, representative or office.

ELKAY does not warrant the recommendations given within for their fitness for use, performance, efficacy or safety. Users are responsible for certification of use of their product and for complying with local legislation. Suggestions of use shall not be taken as inducements to infringe any patents or grant any license under a valid patent and are provided for illustrative purposes only.

Internal References PS/Ref/03/01 DX60101